



MANUFACTURERS OF
ELECTRICAL INSULATION MATERIALS
 INSULATING COMPONENTS FOR
 POWER SYSTEMS EQUIPMENT

TheGundCompany, Inc
 St. Louis, Missouri—USA
 TEL-314.423.5200
 FAX-314.423.9009

MATERIAL DATA SHEET

Item: Conolite Glass Insulation

Description: A glass coated insulation material commonly used as turn insulation in large power generators. The Red Epoxy was designed for use in intermittent steam generators and will exhibit greater long-term temperature resistance than the Green Polyester grade. The Red Epoxy is no longer manufactured, but the data is made available for reference only. Both materials had relative temperature indices of 130 °C.

Availability: Thickness: English units SI Units
 Red Epoxy: 0.012" and .005" .31mm and .13mm
 Green Polyester: .005" .13mm

Fabricated Parts: The Gund Company custom fabricates insulation materials to the exact specifications and drawings of our customers.

Key Characteristics:	Test Method	Units - English (SI)	Typical Values
Tensile Strength (crosswise)	D-638	psi (MPa)	35,892 (248)
Tensile Strength (lengthwise)	D-638	psi (MPa)	35,690 (246)
Tensile Modulus (crosswise)	D-638	psi x 10	19.1
Tensile Modulus (lengthwise)	D-638	psi x 10	19.8
Flexural Strength (crosswise)	D-695, (flatwise)	psi (MPa)	62,829 (433)
Flexural Strength (lengthwise)	D-790	psi (MPa)	76,685 (529)
Modulus of Elasticity (crosswise)	D-790	psi x 10	1.95
Modulus of Elasticity (lengthwise)	D-790	psi x 10	2.63
Compressive Strength	D-695	psi (MPa)	53,400 (368)
IZOD Impact Strength	D-256	ft-lbs/in	33.0
Barcol Hardness			68
Water Absorption	D-570	%	.44
Dielectric Strength	D-149	V/mil (kV/mm)	620 (24.2)
Arc Resistance	D-495	sec	152
Dissipation Factor	D-150		.018
Dielectric Constant	D-150		4.99
Loss Index	D-150		.09
Volume Resistivity	D-257	Ohms/cm	866
Surface Resistivity	D257	MOhms	1,600

All of the information, suggestions, and recommendations herein are based upon tests and data believed to be accurate; however, the final decision regarding the suitability of any material described herein for the use contemplated, the manner of such use, and whether the use infringes any patents is the sole responsibility of the user. There is no warranty, expressed or implied, including, without limitation, warranty of merchantability or fitness for a particular purpose. Under no circumstances shall we be liable for incidental or consequential losses or damages.

All of the information, suggestions, and recommendations pertaining to the properties and uses of the products herein are based upon tests and data believed to be accurate; however, the final termination regarding the suitability of any material described herein for the use contemplated, the manner of such use, and whether the user infringes any patent is the sole responsibility of the user. There is no warranty, expressed or implied, including, without limitation, warranty of merchantability or fitness for a particular purpose. Under no circumstances shall we be liable for incidental or consequential loss or damage.