



RotoGuard TIB: Instructions for Storage & use.

THE GUND COMPANY

MANUFACTURERS & FABRICATORS OF ENGINEERED MATERIAL SOLUTIONS

ATTENTION: Read Before Using

Storage and Shelf Life:

- » Refrigeration is required. Gund RotoGuard TIB is a “B” Stage epoxy.
- » Shelf life is minimum 45 days from receipt when stored in a clean, dry location at 40 °F (4.5 °C) until use.
- » For best results, remove from cold storage 30 minutes prior to use and let warm up in ambient conditions. For optimum tackiness, ideal working temperature is between 65 °F to 80 °F (18.5 °C to 26.5 °C).
- » RotoGuard TIB from The Gund Company should be refrigerated when not in use.

Installation:

- » Remove the release liner quickly, peeling it at approximately 45° angle.
- » Peeling release liner fast when material is cold may cause some adhesive to remain on release liner. See storage and shelf life for additional instructions.
- » Peeling release liner slowly when material is at warmer temperatures may “string” adhesive between substrate and release liner.



For additional information or questions contact us today.

(314) 423- 5200 RotoGuard@thegundcompany.com