



THE GUND COMPANY

MANUFACTURERS & FABRICATORS OF ENGINEERED MATERIAL SOLUTIONS

Threaded Rods & Nuts

Item:	Fiberglass Reinforced Vinyl Ester Threaded Rods & FRP Nuts
Availability:	Threaded Rods & Nuts - Diameters: 0.375" / 0.50" / 0.625" / 0.75" / 1.0"
Fabricated Parts:	The Gund Company custom fabricates insulation materials to the exact specifications and drawings specified by our customers.

Key Property	ASTM Test	Units	3/8" 16 UNC	1/2" 13 UNC	5/8" 11 UNC	3/4" 16 UNC	1" 8 UNC
Ultimate Thread Shear Capacity Using Standard Square Nut ^{1,2,6}	--	lbs	1,000	2,000	3,100	4,500	6,200
Maximum Ultimate Design Tensile Load Using Square Nut ^{1,2,5,6}	--	lbs	800	1,600	2,480	3,600	4,960
Flexural Strength ^{1,2}	ASTM D-790	psi	60,000	60,000	60,000	60,000	60,000
Flexural Modulus ^{2,3}	ASTM D-790	10 ⁶ psi	2.0	2.0	2.0	2.5	2.75
Compressive Strength (LW) ^{2,3}	ASTM D-695	psi	55,000	55,000	55,000	55,000	60,000
Ultimate Transverse Shear ^{2,3}	ASTM B-565	load lb	4,200	7,400	11,600	17,200	27,400
Transverse Shear Yield ^{2,3}	--	load lb	2,100	3,300	4,500	7,500	12,500
Dielectric Strength ^{2,3}	ASTM D-149	kV/in	40	40	40	40	40
Water Absorption ³	ASTM D-570	%	1	1	1	1	1
Coefficient of Thermal Expansion (LW)	ASTM D-696	10 ⁻⁶ in/in/°F	3.0	3.0	3.0	3.0	3.0
Torque Strength - Using Square Nut w/ SAE 10x30 Motor Oil ^{2,4,5,6}	Ultimate	ft-lb	8	15	33	50	115
	Recommended	ft-lb	4	8	16	24	50
Stud Weight ³	--	lb/ft	0.76	0.129	0.209	0.315	0.592
Flammability	ASTM D-635	--	--	--	--	--	--
Thickness - Square Nut	--	in	0.437	0.562	0.688	0.813	1.062
Width - Square Nut	--	in	0.668	0.875	1.062	1.250	1.625

LW = Lengthwise

¹Applies to single unit only; multiple nuts do not yield corresponding results

²Ultimate strength values are averages obtained during testing

³Values are based on unthreaded rod

⁴Torque results are dependent on several variable factors including lubricant used, the length of stud between nuts, alignment, washer surfaces, etc.

Therefore, if such results of torque tightening are important, it is vital that torque limits be determined experimentally for the exact installation conditions.

⁵Appropriate safety factors must be applied

⁶Properties apply to stud used with square nut

AS9100C Certified | ISO/AS9100 Certified QMS | RoHS Compliant | ITAR Compliant

All of the information, suggestions and recommendations pertaining to the properties and uses of the products herein are based upon tests and data believed to be accurate; however, the final determination regarding suitability of any material described herein for the contemplated, the manner of such use, and whether the use infringes any patents is the sole responsibility of the user. There is no warranty, expressed or implied, including, without limitation warranty of merchantability or fitness for a particular purpose. Under no circumstances shall we be liable for incidental or consequential loss or damage.