



THE GUND COMPANY

MANUFACTURERS & FABRICATORS OF ENGINEERED MATERIAL SOLUTIONS

TRANSFORMER SPACER ROD COMPARATIVE DATA High Temperature Spacer Rods




Grades N155, N180, and N220 are high temperature pultruded glass fiber reinforced thermoset resin rods that provides outstanding performance in demanding applications.

- Excellent mechanical strength
- Long term thermal stability
- RoHS Compliant
- Cost effective solution

Typical applications for Grade N155, N180, and N220 include spacer rods for dry type transformers as pictured to the right. These grades have been tested and listed by UL per UL 1446-Standard for systems of Insulation Materials for compatibility with 155 °C, 180 °C, and 220 °C insulation systems. Custom sizes and shapes are available upon request.

Cut to size spacer rods may be kitted along with other fabricated parts, including, but not limited to winding bobbins, flexible N200F sheet material, G-Flex APA flexible laminate for core and inter-coil insulation, Nomex® & G-Flex YT510 high temperature Aramid paper for conductor wrapping and layer insulation, 3M® Layer Insulation, and insulating tapes.



Item:	Availability
Rods:	Dogbones, Rectangles, and Bars (upon request)
Parts:	Fabricated parts, per customer drawings & specifications
Shapes:	<div style="display: flex; justify-content: space-around; align-items: center;"> <div style="text-align: center;">  Rectangles </div> <div style="text-align: center;">  Squares </div> <div style="text-align: center;">  Dogbones </div> </div>



THE GUND COMPANY

MANUFACTURERS & FABRICATORS OF ENGINEERED MATERIAL SOLUTIONS

Item:	High Temperature Spacer Rods, Grades N155, N180, and N220
Description:	<p>High temperature spacer rods are commonly used in applications where mechanical strength and outstanding dielectric strength are required. N155 is available for Class F applications, N180 for Class H applications, while N220 is available for Class R applications. High Temperature spacer rods can handle the high temperature environments of many demanding applications.</p> <p>*Common profiles for high temperature spacer rods can be found on the following pages.</p>

Key Characteristics	Test Method	Units - English (SI)	Typical Values N155	Typical Values N180	Typical Values N220
Standard Color	--	--	White	Light Grey	Natural/Beige
Specific Gravity	ASTM D-792	--	1.9	1.9	1.9
Water Absorption (1/8" thick)	ASTM D-570	%	0.2	0.15	0.15
Tensile Strength	ASTM D-638	psi (MPa)	60,000 (414)	80,000 (551)	80,000 (551)
Compressive Strength	ASTM D-695	psi (MPa)	Axial	45,000 (310)	60,000 (414)
			Transverse	15,000 (103)	15,000 (103)
Flexural Strength	ASTM D-790	psi (MPa)	80,000 (552)	90,000 (621)	90,000 (621)
Shear Strength (In Plane)	ASTM D-3914	psi (MPa)	3,000 (21)	3,000 (21)	3,000 (21)
IZOD Impact Strength	ASTM D-256	ft-lbs/in	40	40	40
Arc Resistance	ASTM D-495	Seconds	130	180	180
Breakdown Voltage (Parallel Pin)	ASTM D-149 (Condition A - Oil)	kV	70	70	70
Relative Temperature Index	UL 746B	°C	155	180	220



THE GUND COMPANY

MANUFACTURERS & FABRICATORS OF ENGINEERED MATERIAL SOLUTIONS

Item:	High Temperature Spacer Sticks, Grades N155, N180, and N220
Description:	High Temperature spacer rods are commonly used in applications where mechanical strength and outstanding dielectric strength are required. The chart below compares several grades of High Temperature spacer rods.

Key Characteristics	Test Method	Units - English (SI)	Typical Values NTR-N220	Typical Values SG-200	Typical Values Supersil
Standard Color	--	--	Natural/Beige	Tan	Grey
Specific Gravity	ASTM D-792	--	1.9	1.85	1.95
Water Absorption (1/8" thick)	ASTM D-570	%	0.15	0.15	0.3
Tensile Strength	ASTM D-638	psi (MPa)	80,000 (551)	70,000 (485)	70,000 (485)
Compressive Strength	ASTM D-695	psi (MPa)	Axial	60,000 (414)	40,000 (275)
			Transverse	15,000 (103)	14,000 (97)
Flexural Strength	ASTM D-790	psi (MPa)	90,000 (621)	80,000 (552)	70,000 (483)
Shear Strength (In Plane)	ASTM D-732	psi (MPa)	3,000 (21)	3,000 (21)	N/A
IZOD Impact Strength	ASTM D-256	ft-lbs/in	40	40	30
Arc Resistance	ASTM D-495	Seconds	180	150	120
Breakdown Voltage (Parallel Pin)	ASTM D-149 (Condition A - Oil)	kV	70	70	50
Relative Temperature Index	UL 746E	°C	220	220	N/A




THE GUND COMPANY


MANUFACTURERS & FABRICATORS OF ENGINEERED MATERIAL SOLUTIONS

Size (in) width x height	Feet / Package	Length/Rod (ft)	Molded Tolerance
1/4 x 3/8	1080	9'	+0.010"
3/8 x 3/8	810	9'	+0.010"
3/8 x 1/2	576	9'	+0.010"
3/8 x 5/8	432	9'	+0.010"
3/8 x 3/4	360	9'	+0.010"
3/8 x 1	288	9'	+0.010"
1/2 x 1/2	432	9'	+0.010"
1/2 x 5/8	324	9'	+0.010"
1/2 x 3/4	270	9'	+0.015"
1/2 x 1	216	9'	+0.015"
5/8 x 3/4	225	9'	+0.015"
5/8 x 7/8	180	9'	+0.015"
3/4 x 1	144	9'	+0.015"
Size (in) width x height	Feet / Package	Length/Rod (ft)	Molded Tolerance
1/4 x 1/4	1620	9'	+ 0.010"
1/4 x 3/8	1080	9'	+ 0.010"
1/4 x 1/2	864	9'	+ 0.010"
1/4 x 5/8	648	9'	+ 0.010"
1/4 x 3/4	540	9'	+ 0.010"
1/4 x 1-3/16	324	9'	+ 0.010"
5/16 x 5/16	972	9'	+ 0.010"
5/16 x 1/2	648	9'	+ 0.010"
5/16 x 1	324	9'	+ 0.010"
3/8 x 3/8	720	9'	+ 0.010"
3/8 x 1/2	576	9'	+ 0.010"
3/8 x 5/8	432	9'	+ 0.010"
3/8 x 3/4	360	9'	+ 0.010"
7/16 x 1/2	504	9'	+ 0.010"
1/2 x 1/2	432	9'	+ 0.010"
1/2 x 5/8	324	9'	+ 0.010"
1/2 x 3/4	270	9'	+ 0.015"
1/2 x 1-3/8	162	9'	+ 0.015"
9/16 x 9/16	315	9'	+ 0.015"
9/16 x 1	180	9'	+ 0.015"
9/16 x 1-1/8	135	9'	+ 0.015"
5/8 x 3/4	225	9'	+ 0.015"
3/4 x 1	144	9'	+ 0.015"
1-1/4 x 1-1/4	54	9'	+ 0.015"

N155 or N220
Dogbones



N155 or N220
Rectangles & Squares



Data supplied above are typical values and are not to be considered specification values. All of the information, suggestions and recommendations pertaining to the properties and uses of the products herein are based upon tests and data believed to be accurate; however, the final determination regarding suitability of any material described herein for the contemplated application, the manner of such use, and whether the use infringes any patents is the sole responsibility of the user. There is no warranty, expressed or implied, including, without limitation warranty of merchantability or fitness for a particular purpose. Under no circumstances shall we be liable for incidental or consequential loss or damage.