

# THE GUND COMPANY

MANUFACTURERS & FABRICATORS OF ENGINEERED MATERIAL SOLUTIONS

## G-Flex Meta-Aramid Paper YT510

## **Insulation Aramid Papers**

G-Flex YT510 is a group of insulation aramid papers that offer high dielectric strength, mechanical toughness, flexibility, and resilience. It is available in thicknesses ranging from 0.05 mm to 0.75 mm (2 mil to 30 mil). G-Flex YT510 is widely used in a majority of electrical equipment applications. It can be used in almost any electrical product where an electrical insulation sheet form is necessary. G-Flex YT510 exhibits exceptional electrical, mechanical, and thermal properties comparable to all alternatives today. The table below shows the typical data for significant electrical, mechanical, and thermal properties by standard thickness.

#### The UL File number is E521153. G-Flex YT510 meets ANSI/NEMA FI 3-2004 - superseding MIL-1-24204A.

The Gund Company custom fabricates insulation materials to the exact specifications and drawings specified by our customers. We offer our customers the proper product for their specific application. A variety of dimensions and diameter sizes are available. Additional thicknesses are available upon request.

|            |                           | ASTM        | STM TYPICAL VALUES         |             |             |             |               |             |             |             |             |             |
|------------|---------------------------|-------------|----------------------------|-------------|-------------|-------------|---------------|-------------|-------------|-------------|-------------|-------------|
| PROPERTIES |                           | Test Method | Units                      | YT510RL0002 | YT510RL0003 | YT510RL0005 | YT510RL0007.5 | YT510RL0010 | YT510RL0012 | YT510RL0015 | YT510RL0020 | YT510RL0030 |
| PHYSICAL   | Standard Thickness        |             | mil                        | 2           | 3           | 5           | 7             | 10          | 12          | 15          | 20          | 30          |
|            | Standard Thickness        |             | mm                         | 0.05        | 0.08        | 0.13        | 0.18          | 0.25        | 0.3         | 0.38        | 0.51        | 0.76        |
|            | Base Weight               | ASTM D149   | g/m²                       | 41.5        | 63          | 116         | 170           | 252         | 291         | 376         | 510         | 710         |
|            | Density                   |             | g/cc                       | 0.79        | 0.8         | 0.9         | 0.94          | 0.99        | 1           | 0.99        | 1           | 0.93        |
|            | Tensile Strength: MD      | ASTM D828   | N/cm                       | 41          | 66          | 130         | 200           | 290         | 340         | 420         | 500         | 650         |
| MECHANICAL | Tensile Strength: CD      | ASTM D828   | N/cm                       | 41          | 29          | 60          | 75            | 120         | 155         | 250         | 345         | 450         |
|            | Elongation: MD            | ASTM D828   | %                          | 7.5         | 9.5         | 10.5        | 11.5          | 11.5        | 10.5        | 12          | 13          | 13          |
|            | Elongation: CD            | ASTM D828   | %                          | 7           | 9.5         | 11.5        | 12.5          | 13.5        | 10.5        | 13          | 13          | 13          |
|            | Elmendorf Tear: MD        | TAPPI 414   | N                          | 0.65        | 1.05        | 2.2         | 3.5           | 5           | 6.5         | 10          | 13          | N/A         |
|            | Elmendorf Tear: CD        | TAPPI 414   | N                          | 1.1         | 2.05        | 3.8         | 4.8           | 6           | 8           | 13.5        | 16          | N/A         |
|            | Initial Tear Strength: MD | ASTM D1004  | N                          | 16.41       | 25.07       | -           | -             | 79.04       |             | 114.63      | -           | -           |
|            | Shrinkage: MD at 300°C    | IEC 60819-2 | %                          | 3.5         | 3.5         | 3           | 3             | 3           | 3           | 3           | 3           | 3           |
|            | Shrinkage: CD at 300°C    | IEC 60819-2 | %                          | 3           | 3           | 2.5         | 2.5           | 2.5         | 2.5         | 2.5         | 2           | 2           |
|            |                           |             |                            |             |             |             |               |             |             |             |             |             |
| ELECTRICAL | Breakdown Voltage         | ASTM D149   | kV                         | 0.81        | 1.25        | 2.7         | 3.9           | 6.3         | 6.4         | 9           | 8           | 13.5        |
|            | Dielectric Strength       | ASTM D149   | V/mil                      | 406         | 406         | 508         | 533           | 635         | 560         | 580         | 533         | 482         |
|            | Dielectric Strength       | ASTM D149   | kV/mm                      | 16          | 16          | 20          | 21            | 25          | 22          | 23          | 21          | 18          |
|            | Full Wave Impulse         | ASTM D3426  | V/mil                      | 1,000       | 1,000       | 1,400       | 1,400         | 1,600       | N/A         | 1,400       | 1,400       | 1,250       |
|            | Full Wave Impulse         | ASTM D3426  | kV/mm                      | 39          | 39          | 55          | 55            | 63          | N/A         | 55          | 55          | 49          |
|            | Dielectric Constant       | ASTM D150   | 60 Hz                      | 1.6         | 1.6         | 2.4         | 2.7           | 2.7         | 2.9         | 3.2         | 3.4         | 3.7         |
|            | Dissipation Factor        | ASTM D150   | 60 Hz (x10 <sup>-3</sup> ) | 4           | 5           | 6           | 6             | 6           | 7           | 7           | 7           | 7           |

The data supplied are typical values. They are not to be considered specification values. All of the information, suggestions, and recommendations about these properties and uses of the products herein are based on tests and data believed to be accurate; however, the final determination regarding the suitability of any material described herein for the contemplated application, the manner of such use, and whether the use infringes any patents is the sole responsibility of the user. There is no warranty - expressed or implied - including, without limitation, warranties of merchantability or fitness for a particular purpose. Under no circumstances shall we be liable for incidental or consequential loss or damage.



## THE GUND COMPANY

MANUFACTURERS & FABRICATORS OF ENGINEERED MATERIAL SOLUTIONS

#### MARKETS



Switchgear

Electronics

**Power Generators** 

**Motor Applications** 

Transformers

**Metals Processing** 

**Electric Vehicles** 

Military/Aerospace

Oil & Gas

Medical

Space

### **OUR EXPERTISE IS YOUR COMPETITIVE ADVANTAGE**

The Gund Company provides a wide range of material solutions from rigid, glass epoxy composites to high-temperature, silicone sponges.

We take a consultative approach to understanding your application by working with your engineers and buyers to find materials that fit the application. By understanding the most important material properties, we often find cost-reduction opportunities. Our Application Engineering Teams have decades of material experience and look forward to working with you on your upcoming project.

#### **Material Families:**

- Thermoset Rigid Laminates and Composites
- Flexible Laminates, Papers, Films, and Felts
- Thermoplastic Materials
- Elastomeric Materials

#### **Our Manufacturing Capabilities Include:**

- Compression Molding
- Pultrusion
- Filament & Convolute Wound Tube
- Infusion & B-Stage Composites Lay-up and Molding
- Injection Molding
- Extrusion of Thermoplastics

**Our Engineering Capabilities Include:** 

- Custom Material Development
- Resin Formulation
- Laboratory Testing
- Comparative Materials Evaluation



### THE GUND COMPANY GLOBAL FOOTPRINT - LOCAL SERVICE



www.thegundcompany.com | World HQ: 314-492-4800