



THE GUND COMPANY

MANUFACTURERS & FABRICATORS OF ENGINEERED MATERIAL SOLUTIONS

Acrylic Amorphous Commodity Plastic

Acrylic (known as Plexiglas) is a transparent thermoplastic with outstanding strength, stiffness, and optical clarity. Acrylic sheets are easy to fabricate and bond well with adhesives. Because it's a thermoplastic, it can soften under extremely high temperatures. That also makes it easy to fabricate into virtually any shape. It is incredibly durable, and some grades are UV-resistant. It is a suitable solution over a broad temperature range and has superior weathering properties compared to other plastics.

The Gund Company custom fabricates insulation materials to the exact specifications and drawings specified by our customers. We offer our customers the proper product for their specific application. A variety of dimensions and diameter sizes are available. Product colors vary according to material type.

		ISO/IEC			ASTM		
PROPERTIES		Test Method	Units	Typical Values	Test Method	Units	Typical Values
PHYSICAL	Specific Gravity				ASTM D792		1.19
	Water Absorption: 24 hrs. at 73°F		%	0.20	ASTM D570	%	0.20
THERMAL	Forming Temperature		°C	149		°F	Approx. 300
	Heat Deflection Temperature (264 PSI)		°C	91	ASTM D648	°F	195
	Vicat Softening Point		°C	105	ASTM D1525	°F	220
	Max Continuous Service Temperature in Air		°C	71		°F	160
	Coefficient of Linear Thermal Expansion		µm/m·°C	72	ASTM D696	µin/in·°F	40
	Thermal Conductivity		W/m·K	0.19	Cenco-Fitch	BTU-in/ft²·hr·°F	1.30
	Flammability: Burning Rate		mm/min	25	ASTM D635	in/min	1
	Self-Ignition Temperature		°C	455	ASTM D1929	°F	850
	Specific Heat at 77°F		J/Kg·K	1,470		BTU/lb·°F	0.35
MECHANICAL	Smoke Density Rating		%	5	ASTM D2843	%	5
	Ultimate Tensile Strength				ASTM D638	PSI	10,000
	Elongation at Break				ASTM D638	%	5
	Tensile Modulus				ASTM D638	KSI	400
	Flexural Strength				ASTM D790	PSI	17,000
	Flexural Modulus				ASTM D790	KSI	480
	Compressive Strength at Yield				ASTM D695	PSI	17,000
	IZOD Impact Strength: Milled, Notched				ASTM D256	ft-lb/in	0.40
	Rockwell Hardness: M Scale				ASTM D785		93
ELECTRICAL	Barcol Hardness				ASTM D2583		48
	Dielectric Strength Short Time (0.125")				ASTM D149	V/mil	430
	Dielectric Constant: 60 Hz				ASTM D150		3.60
	Dielectric Constant: 1,000 Hz				ASTM D150		3.30
	Dielectric Constant: 1 MHz				ASTM D150		2.80
	Dissipation Factor: 60 Hz				ASTM D150		0.06
	Dissipation Factor: 1,000 Hz				ASTM D150		0.04
	Dissipation Factor: 1 MHz				ASTM D150		0.02
	Volume Resistivity				ASTM D257	Ohm-cm	10 ¹⁶
OPTICAL	Surface Resistivity				ASTM D257	Ohms	10 ¹⁵
	Refractive Index				ASTM D542		1.49
	Transmission: Visible				ASTM D1003	%	92

The data supplied are typical values. They are not to be considered specification values. All of the information, suggestions, and recommendations about these properties and uses of the products herein are based on tests and data believed to be accurate; however, the final determination regarding the suitability of any material described herein for the contemplated application, the manner of such use, and whether the use infringes any patents is the sole responsibility of the user. There is no warranty - expressed or implied - including, without limitation, warranties of merchantability or fitness for a particular purpose. Under no circumstances shall we be liable for incidental or consequential loss or damage.