

Laminate



ALTHERM 550

- High temperature resistance
- Excellent electrical insulation properties
- Excellent flammability classification
- Low water adsorption

	Unit	Value	Test norm
Mechanical properties			
Flexural strength	MPa	150	ISO 178
Compressive strength $\perp$ at 23°C	MPa	450	ISO 604
Tensile strength	MPa	130	ISO 527
Electrical properties			
Insulation resistance after immersion in water	Ohm	1.00E+12	IEC 62631-3-3
Electric strength $\perp$ 90°C in oil	kV/mm	8	IEC 60243-1
Arc resistance	s	180	ASTM D 495
Comparative tracking index CTI		600	IEC 60112
Thermal properties			
Temperature index (TI)	TI	220	IEC 60216
Thermal conductivity	W/m.K	0.3	ISO 8301
Linear expansion coefficient //	1.0E-6/K	12	ISO 11359-2
Physical properties			
Density	g/cm ³	1.85	ISO 1183
Flammability		V-0	UL 94
Water absorption	%	0.1	ISO 62

Description

Altherm 550 is an insulating laminate made of fine weave glass fabric bonded with silicone resin especially developed for applications in aluminium smelters.

RoHS Directive

Hazardous products listed in the EU-directive 2011/65/EU (RoHS-directive), annex II and amendment 2015/863/EU are not used as ingredients in this material.

Color

White

Applications

Different parts of aluminium smelters:

- busbar electrical insulation
- superstructure support
- pot room thermal and electrical insulation
- pot conductor insulation

Form of delivery

Sheet formats 1170 x 1070 mm, 2070 x 1070 mm
Size tolerance 0 / - 30 mm

Thickness range 0.2 to 30 mm
Thickness tol. acc. to DIN EN 60893-3-6

Also available as panels or machined parts.
Other dimensions and thicknesses on request.

Machining

Machining with carbide or diamond tools.
For water jet cutting we recommend adding silica sand to the water and drill through-holes prior to machine.

The data supplied are typical values. They are not to be considered specification values. All of the information, suggestions, and recommendations about these properties and uses of the products herein are based on tests and data believed to be accurate; however, the final determination regarding the suitability of any material described herein for the contemplated application, the manner of such use, and whether the use infringes any patents is the sole responsibility of the user. There is no warranty - expressed or implied - including, without limitation, warranties of merchantability or fitness for a particular purpose. Under no circumstances shall we be liable for incidental or consequential loss or damage.

VRI Composites custom fabricates insulation materials to the exact specifications and drawings specified by our customers. We offer our customers the proper product for their specific application. A variety of dimensions and diameter sizes are available. Product colors vary according to material type.

VRIR 03/2026