

Round Tubes

CANEVASITE VRI-BAT T



- Very good mechanical properties
- Allows machining of finest details
- Very fine weave > 40 threads/cm²
- Similar to PF CC 24 acc. to DIN EN 61212-3-1

	Unit	Value	Test norm
Mechanical properties			
Flexural strength	MPa	140	ISO 178
E-Modulus	MPa	6500	ISO 178
Compressive strength axial	MPa	210	ISO 604
Compressive strength radial	MPa	300	ISO 604
Cohesion between layers	MPa	230	EN 61212-2
Electrical properties			
Insulation resistance after immersion in water	Ohm	1.0E+8	IEC 60167
Breakdown voltage //, 90°C in oil	kV	13	IEC 20243-1
Electric strength ⊥, 90°C in oil	kV/mm	3	IEC 20243-1
Thermal properties			
Temperature index (TI)	°C	120	IEC 60216
Physical properties			
Density	g/cm ³	1,25 – 1,35	ISO 1183
Water absorption 24 h 23°C	Mg/cm ²	3,0	ISO 62

Description

Canevasite VRI-BAT T consists of phenolic resin with a reinforcement of cotton batiste fabric.

RoHS Directive

Hazardous products listed in the EU-directive 2011/65/EU (RoHS-directive), annex II and amendment 2015/863/EU are not used as ingredients in this material.

Colour

Brown

Application

Rings for high-precision ball bearing cages
Rings for miniature ball bearing cages
Rings for high-speed bearings in textile machinery

Form of delivery

This type will be supplied in form of tubes and machined parts out of tubes. The standard diameter range lasts from 2,6 mm to 450 mm.

The length is related to the diameter, standard lengths are approx. 500/1.000/1500 mm.

Other diameters and lengths on request.

Tolerances acc. to DIN EN 61212-3-1

The data supplied are typical values. They are not to be considered specification values. All of the information, suggestions, and recommendations about these properties and uses of the products herein are based on tests and data believed to be accurate; however, the final determination regarding the suitability of any material described herein for the contemplated application, the manner of such use, and whether the use infringes any patents is the sole responsibility of the user. There is no warranty - expressed or implied - including, without limitation, warranties of merchantability or fitness for a particular purpose. Under no circumstances shall we be liable for incidental or consequential loss or damage.

VRI Composites custom fabricates insulation materials to the exact specifications and drawings specified by our customers. We offer our customers the proper product for their specific application. A variety of dimensions and diameter sizes are available. Product colors vary according to material type.

VRIR 02/2026

VRI Composites Deutschland GmbH
www.vri-composites.com

Canevasite VRI-BAT T