

Round Tubes



VETRONITE EGS 102 T

- Exceptionally high mechanical strength at moderate temperature
- Very good electrical properties at high relative humidity
- Corresponds to EP GC 21 according to DIN EN 61212-3-1
- Comparable to NEMA LI-1 Type G-10

	Unit	Value	Test norm
Mechanical properties			
Flexural strength	MPa	400	EN 61212-2
E-Modulus	MPa	20000	ISO 178
Compressive strength axial	MPa	250	EN 61212-2
Cohesion between layers	MPa	450	EN 61212-2
Electrical properties			
Insulation resistance after immersion in water	Ohm	5.0E+6	DIN EN 62631-3-3
Breakdown voltage // 90°C in oil	kV	75	IEC 60243-1
Electric strength ⊥ 90°C in oil	kV/mm	15	IEC 60243-1
Permittivity at 1 MHz		5.2	IEC 60250
Dissipation factor at 1 MHz		0.04	IEC 60250
Comparative tracking index CTI	V	250	IEC 60112
Thermal properties			
Temperature index (TI)	°C	130	IEC 60216
Physical properties			
Density	g/cm ³	1.80	ISO 1183
Water absorption 24 h 23°C	mg/cm ²	1.4	ISO 62
Other properties			
Flammability		HB	UL 94

Description

Vetronite EGS 102 T consists of epoxy resin with a reinforcement of glass cloth.

RoHS Directive

Hazardous products listed in the EU-directive 2011/65/EU (RoHS-directive), annex II and amendment 2015/863/EU are not used as ingredients in this material.

Colour

Green

Application

Machine construction
Electro-technics
Fixture construction
High voltage insulating parts

Form of delivery

This type will be supplied in form of tubes and machined parts out of tubes.
Diameter: From 3.5 mm to 450 mm.

The length is related to the diameter, standard length approx. 1000 mm.
Other diameters and lengths on request.

Tolerances acc. to DIN EN 61212-3-1

The data supplied are typical values. They are not to be considered specification values. All of the information, suggestions, and recommendations about these properties and uses of the products herein are based on tests and data believed to be accurate; however, the final determination regarding the suitability of any material described herein for the contemplated application, the manner of such use, and whether the use infringes any patents is the sole responsibility of the user. There is no warranty - expressed or implied - including, without limitation, warranties of merchantability or fitness for a particular purpose. Under no circumstances shall we be liable for incidental or consequential loss or damage.

VRI Composites custom fabricates insulation materials to the exact specifications and drawings specified by our customers. We offer our customers the proper product for their specific application. A variety of dimensions and diameter sizes are available. Product colors vary according to material type.

VRI Composites Deutschland GmbH
www.vri-composites.com

Vetronite EGS 102 T

VRIR 02/2026