

Laminate



VETRONITE EGS 619 CU

- Copper clad laminate
- High pressure laminate with excellent mechanical and electrical properties as a base plate
- Base plate with burning behaviour according to UL 94 level V-0

Base plate properties	Unit	Value	Test norm
Mechanical properties			
Flexural strength	MPa	500	ISO 178
E-modulus	MPa	23000	ISO 178
Flexural strength after 150°C / 1h	MPa	200	ISO 178
Notched impact strength (Charpy), //	kJ/m²	70	ISO 179
Compressive strength // at 23°C	MPa	350	ISO 604
Compressive strength ⊥ at 23°C	MPa	500	ISO 604
Shear strength //	MPa	30	DIN 65148
Tensile strength	MPa	300	ISO 527
Electrical properties			
Insulation resistance after immersion in water	Ohm	1.00E+12	IEC 62631-3-3
Breakdown voltage // 90°C in oil	kV	80	IEC 60243-1
Electric strength ⊥ 90°C in oil	kV/mm	18	IEC 60243-1
Relative permittivity at 1 MHz		4.8	IEC 62631-2-1
Dissipation factor at 1 MHz		0.02	IEC 62631-2-1
Comparative tracking index CTI		250	IEC 60112
Thermal properties			
Temperature index (TI)	TI	130	IEC 60216
Thermal conductivity	W/m·K	0.3	ISO 8301
Linear expansion coefficient //	1.0E-6/K	15	ISO 11359-2
Physical properties			
Density	g/cm³	1.92	ISO 1183
Water absorption	mg/%	12/0.06	ISO 62

Description

Vetronite EGS 619 CU is a copper clad material. The base plate is an insulating laminate made of fine weave glass fabric bonded with special epoxy resin. It has a temperature index of 155°C.

RoHS Directive

Hazardous products listed in the EU-directive 2011/65/EU (RoHS-directive), annex II and amendment 2015/863/EU are not used as ingredients in this material.

Colour

Light green

Applications

CT-Scanners
MRI-Scanners

Machining

Machining with carbide or diamond tools.
For water jet cutting we recommend adding silica sand to the water and drill through-holes prior to machine.

Form of delivery

Sheet formats 1170 x 1070 mm; 1270 x 1070 mm
Size tolerance 0 / - 30 mm
Copper thicknesses one or two-sided: 105 µm, 175 µm, 400 µm

Thickness range 0.4 to 6 mm
Thickness tol. acc. to DIN EN 60893-3-2

Other dimensions, thicknesses or copper thicknesses on request.

The data supplied are typical values. They are not to be considered specification values. All of the information, suggestions, and recommendations about these properties and uses of the products herein are based on tests and data believed to be accurate; however, the final determination regarding the suitability of any material described herein for the contemplated application, the manner of such use, and whether the use infringes any patents is the sole responsibility of the user. There is no warranty - expressed or implied - including, without limitation, warranties of merchantability or fitness for a particular purpose. Under no circumstances shall we be liable for incidental or consequential loss or damage.

VRI Composites custom fabricates insulation materials to the exact specifications and drawings specified by our customers. We offer our customers the proper product for their specific application. A variety of dimensions and diameter sizes are available. Product colors vary according to material type.

VRIR 03/2026