

Round Tubes



VETRONITE EGS T23 T

- High mechanical strength at elevated temperatures
- Excellent electrical properties
- High glass transition temperature
- Resistance against heat peaks higher than 200°C
- Very good chemical resistance
- Similar to EP GC 22 acc. to DIN EN 61212-3-1

Description

Vetronite EGS T23 T consists of special high temperature epoxy resin with a reinforcement of glass cloth.

RoHS Directive

Hazardous products listed in the EU-directive 2011/65/EU (RoHS-directive), annex II and amendment 2015/863/EU are not used as ingredients in this material.

Colour

Grey

Application

Insulation tubes in high-voltage applications at elevated temperatures
Chemical industry

	Unit	Value	Test norm
Mechanical properties			
Flexural strength	MPa	330	EN 61212-2
E-Modulus	MPa	20000	ISO 178
Compressive strength axial	MPa	220	EN 61212-2
Cohesion between layers	MPa	400	EN 61212-2
Electrical properties			
Insulation resistance after immersion in water	Ohm	1.0E+7	DIN EN 62631-3-3
Breakdown voltage // 90°C in oil	kV	65	IEC 60243-1
Electric strength ⊥ 90°C in oil	kV/mm	12	IEC 60243-1
Comparative tracking index (CTI)	°C	200	IEC 60112
Physical properties			
Density	g/cm ³	1.85	ISO 1183
Water absorption 24 h 23°C	mg/cm ²	1.0	ISO 62
Thermal properties			
Temperature index (TI)	°C	180	IEC 60216

Form of delivery

This type will be supplied in form of tubes and machined parts out of tubes. The standard diameter range lasts from 8 mm to 450 mm.

The length is related to the diameter, standard length approx. 1.000 mm. Other diameters and lengths on request.

Tolerances acc. to DIN EN 61212-3-1

The data supplied are typical values. They are not to be considered specification values. All of the information, suggestions, and recommendations about these properties and uses of the products herein are based on tests and data believed to be accurate; however, the final determination regarding the suitability of any material described herein for the contemplated application, the manner of such use, and whether the use infringes any patents is the sole responsibility of the user. There is no warranty - expressed or implied - including, without limitation, warranties of merchantability or fitness for a particular purpose. Under no circumstances shall we be liable for incidental or consequential loss or damage.

VRI Composites custom fabricates insulation materials to the exact specifications and drawings specified by our customers. We offer our customers the proper product for their specific application. A variety of dimensions and diameter sizes are available. Product colors vary according to material type.

VRIR 02/2026